



APPLICATIONS INSTRUCTIONS

Firefree Exterior Topcoat (“FfE”) is a premium, 100% acrylic exterior protective coating and its application is similar to applying any acrylic exterior paint (except for the thickness recommended by Firefree Coatings, which needs to be precisely complied with for adequate performance. FfE is listed and inspected by the International Code Council (“ICC”).

FfE is to be used exclusively over surfaces previously coated with Firefree Class A (“FfA”) or Firefree 88 (“Ff88”), to improve the durability of such products if used in exterior applications in strict compliance with Firefree Coatings (“Firefree”)’s recommendations. There can be no substitution of FfE as this proprietary acrylic topcoat has passed the weatherization test (ASTM D2898, method B) over the Firefree intumescent coatings. Any substitution would void any warranty express or implied.

It is the sole responsibility of the customer to choose a qualified applicator for the Product and ensure that such applicator applies the Product in strict compliance with the Application Instructions and applies the recommended thickness.

SURFACE PREPARATION

FfE is designed to be applied on top of Firefree Class A or Firefree 88. The underlying coat of FfA or Ff88 must be thoroughly dry before FfE is applied (see FfA or Ff88 Application Instructions as applicable). All surfaces must be covered with FfA or Ff88. Such FfA or Ff88 covered surface must be dry and clean before FfE is applied.

APPLICATION EQUIPMENT

FfE can be applied by airless sprayer, roller or brush. Spraying and back rolling is recommended on new flat work. Stir thoroughly before and during use. Maintain a wet edge to avoid lap marks. **DO NOT THIN.**

Spray (Airless): Recommended low pressure tip size; use .013” (0.033 cm) - .015 (0.038 cm). Follow recommendation of pressure range set by tip manufacturer. heavy duty 4” to 12 “(10.16 cm to 30.48 cm) fan width recommended.

Roller: use 3/8” - 3/4” (9.53 - 19.05 mm) nap synthetic cover for heavy application. Other rollers may be used depending on desired finish.

Brush: use a Nylon/Polyester Brush. A laying on technique will reduce the brush marking.

THICKNESS/COVERAGE

The recommended thickness for FfE is: 12 mils wet / 6 mils dry, **MUST BE applied in two coats at 6 mils wet / 3 mils dry per coat.** The coverage rate is 110 sq ft/gal (2.70m²/L) at 6 mils dry. The dry film thickness recommended by Firefree needs to be precisely complied with for adequate performance. The wet film thickness should be checked using a wet film thickness gauge.



Read instructions on gauge for proper use.

DRYING TIME

Drying times depend on several factors, including those below, and can vary from 4 to 48 hours, or longer for each coat:

- **Temperature.** Do not apply FfE if air and surface temperature is below 50°F (10°C) or above 95°F (35°C).
- **Air movement.**
- **Humidity.** We do not recommend applying the coating if relative humidity exceeds 75%.
- **Method of application.**

For more information, please contact Firefree Coatings.

Make sure that each coat of FfE is **thoroughly dry to the touch** before applying the next coat.

COLOR, FINISH, AND USE OF TOPCOAT OVER FfE

FfE comes in a white color and both standard (white) and (deep) bases, satin finish. Both bases are tintable to most colors. FfE can also be top coated with most premium exterior latex paints to achieve a different color and finish. Contact your local paint store for assistance on tinting or choice of topcoat.

MAINTENANCE

Surfaces which have been coated with FfE should be protected from abuse and abrasion. Damaged surfaces should be repaired and new FfE should be applied to the original recommended dry film thickness.

SAFETY

Avoid contact with eyes, skin and clothing. Do not take internally. Use personal protective clothing, including safety glasses to prevent any particles of paint from entering the eyes. Protective gloves are recommended for prolonged contact exposure. Respiratory protection is recommended, but not required; however, make sure plenty of ventilation is allowed. Protective half masks can be used when painting to prevent breathing paint dust or particles from entering the lungs. Wash thoroughly after handling. Close container after each use. Keep out of reach of children.

For additional safety information consult the Safety Data Sheet for this product.

DISPOSAL

Never pour leftover coating down any sink or drain.

Use up material on the job or seal can and store safely. Do not incinerate. For specific disposal or recycle guidelines, contact your local waste management agency or district. Always attempt to recycle whenever possible.

STORAGE AND TEMPERATURE

FfE cannot be exposed to freezing temperatures or exposed continuously to direct sunlight. FfE needs to be stored at temperatures between 50°F and 85°F (10°C to 29°C). Expected shelf life is two years from date of manufacture (DOM). Product must be kept in storage temperature conditions and in original unopened containers.

ABOUT THE COMPANY

FIREFREE® Coatings, Inc is the leading developer of high-quality fire retardant and fire-resistant intumescent coatings that will help reduce the spread of fire, minimize smoke and toxic gases that would occur during a fire, thus giving occupants extra time to evacuate a building safely and limiting destruction of property. Our products are tested at a third-party accredited International Accreditation Service (IAS) testing laboratory.

Firefree Coatings is deeply committed to human safety and environmental issues and is strongly positioned to meet the increasing demand for fire safety benefits for commercial, governmental, residential, and other advanced markets.

Firefree Coatings is a member of NFPA, ICC and ASTM E-05 Committee.

**Main Office: 8 Commercial Blvd
Toll free: 888-990-3388, (+1) 415-459-6488,
info@firefree.com**



This information is provided "as is" by Firefree® Coatings, Inc. and no representation or expressed or implied warranties or merchantability, fitness for a particular use or of any other nature are made with respect to this information or to any product referred to in this written information. Adding color may increase the VOC limits. For SDS or to consult with a Firefree® Certified Coating Professional call 888-990-3388. To the best of our knowledge, the data contained herein is true and accurate on the date of publication and is subject to change without prior notice. FIREFREE® is a registered trademark of FIREFREE Coatings, Inc. © 2021 Firefree